

垫片密封胶 万能密封



包装

30000090
30000120
30000300
30000230

垫片密封胶 万能密封 90 g
垫片密封胶 万能密封 120 g
垫片密封胶 万能密封 300 g
垫片密封胶 万能密封 230 g

产品配件

13250001
13250002
13250009
13955072

压力胶枪,
压力胶枪特殊款,
空压胶枪,
Press Pack Dosing Tip,

永久塑性, 万能密封
涂胶后无需等待, 可即时装配

该产品适用于机械法兰、变速箱和电机铸件的法兰密封, 冷热表面均可适用。它可提高新旧密封垫 (例如纸, 软木, 毡等) 的密封效果。该产品不含溶剂、不含硅, 无气味, 装配前后均保持永久塑性。它拆卸方便且用量节约, 不腐蚀, 不滴垂, 对大多数燃料、矿物油、水、空气、甲醇和单糖混合物、防冻剂氟碳冷却剂等有良好的抗性。

技术参数

基础成分	聚酯树脂
颜色	蓝色 (荧光)
温度为+20°C时的密度	1,15 g/cm ³
最大粘接缝隙	0,10 mm
依据 Brookfield 在温度+25°C时的粘度	950.000 - 1.650.000 mPa·s
操作温度	+5 至 +35 °C
保存期限	24 个月
耐温性	-50至+200, 短时可达+250 °C
ISSA 编码	75.628.41/42/43
IMPA 编码	815231/32/33

表面预处理

为了达到最佳效果, 涂胶表面需保持清洁、干燥。可使用 WEICON 表面清洁剂进行清洁。

储藏

保存期限: 室温环境下 (+20°C) 可储存至少24个月。

安全与健康

<p>使用WEICON产品时, 需注意产品的物理性、安全性、毒性、生态性的详细参数以及我们EG材料安全数据表 (www.weicon.com) 的具体信息。</p>

提示

本资料中列出的所有产品, 其参数和建议是我们在实验室的测试结果及经验总结, 不得被视为对产品特性的保证。由于每一个用的实际应用情况并不在我们的认知、控制及责任范围内, 我们对这些信息并不承担任何义务。我们保证我们的产品符合并遵守我们销售条款中承诺的高品质、无瑕疵的要求。我们建议用户通过自行试验来论证其希望选用的产品是否符合预期。因用户未遵照指定的操作方法使用产品而造成损失的情况, 用户将独自承担全部责任。

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322
0
info@weicon.de
www.weicon.de

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709
0088
info@weicon.co.za
www.weicon.co.za

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Czech Republic
s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd.
Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730
763
office@weicon.com
www.weicon.com.ro

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it

Plast-o-Seal®



permanently plastic universal sealant
solvent free with no unpleasant odour enables immediate assembly

For sealing the smooth treated flanges of machine, gearbox and motor casing flanges. To improve the performance of both old and new gaskets made from paper, cork, felt etc. Solvent free, free of silicon, odourless, remains permanently plastic, both before and after assembly, easy joint dismantling, non corrosive, No dripping, very good resistance to most fuels, mineral oils, water, air, coolant mixtures based on methanol and glycol, antifreezes, kerosene, fluorocarbon refrigerants etc.

Technical Data

Base	Polyester resin
Colour	Blue (fluorescent)
Specific weight at +20°C (+68°F)	1,15 g/cm³
Max. Gap Bridging	0,10 mm
Viscosity at 25°C (+77°F) according to Brookfield	950.000 - 1.650.000 mPa·s
Processing temperature	+5 to +35 °C
Storage stability	24 months
Temperature resistance	-50 to +200 briefly to +250 °C
ISSA-Code	75.628.41/42/43
IMPA-Code	815231/32/33

Surface pre-treatment

Best results will be achieved on cleaned, degreased parts (use WEICON Surface Cleaner).

Processing

Plast-o-Seal on one surface. No ventilating necessary enables immediate assembly, immediate sealing effect. At low temperatures, carry to +20°C before application.

Storage

Shelf life: min. 24 months at room temperature (+20°C).

Safety and health

<p>When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.</p>

Available sizes:

30000090	Plast-o-Seal® 90 g
30000120	Plast-o-Seal® 120 g
30000300	Plast-o-Seal® 300 g
30000230	Plast-o-Seal® 230 g

Accessories:

13250001	Cartridge Gun,
13250002	Cartridge Gun Special,
13250009	Compressed Air Cartridge Gun,
13955072	Press Pack Dosing Tip,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
 (Headquarters)
 Germany
 phone +49 (0) 251 9322 0
info@weicon.de
www.weicon.de

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
info@weicon.co.za
www.weicon.co.za

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
info@weicon.ae
www.weicon.ae

WEICON South East Asia Pte Ltd
 Singapore
 phone +65 6710 7671
info@weicon.com.sg
www.weicon.com.sg

WEICON Inc.
 Canada
 phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Turkey
 phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON Italia S.r.l.
 Italy
 phone (+39) 0102924871
info@weicon.it
www.weicon.it